10/711,269 Amdt. Dated Oct. 19, 2006 Resp. to Off. Action dated Jul. 20, 2006

## Amendments to the Claims:

Please cancel claims 2-5 and 7.

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims:**

1 (Currently Amended). A golf ball comprising:

a core; and

a cover formed over the core, the cover composed of a thermosetting polyurethane material formed from reactants comprising at least one polyurethane prepolymer and a curative blend consisting essentially of 4,4'-methylenebis-(2,6-diethyl-aniline) 4,4'-methylenebis-(2,6-diethyl)-aniline and a second curing agent selected from the group consisting of N,N'-bis-alkyl-p-phenylenediamine, N,N'-dialkylamino-diphenylmethane with tetrapropoxylated ethylenediamine, liquid aromatic diamine and an aliphatic diamine;

wherein the cover has an aerodynamic surface geometry thereon.

2-5(Canceled).

10/711,269 Amdt. Dated Oct. 19, 2006 Resp. to Off. Action dated Jul. 20, 2006

6 (Currently Amended). A golf ball comprising:

a core comprising a polybutadiene mixture;

a boundary layer formed over the core; and

a cover formed over the boundary layer, the cover composed of a thermosetting polyurethane material formed from reactants comprising a polyester glycol terminated toluene diisocyanate prepolymer with a <u>NCO nitrogen-carbon-oxygen</u> group content ranging from 3.0% to 7.0% and a curative blend consisting essentially of 4,4'-methylenebis-(2,6-diethyl)-aniline 4,4'-methylenebis-(2,6-diethyl-aniline) in an amount of 65 parts per one hundred parts of the curative blend and N,N'-bis-alkyl-p-phenylenediamine with tetrapropoxylated ethylenediamine in an amount of 35 parts per one hundred parts of the curative blend;

wherein the cover has an aerodynamic surface geometry thereon.

7 (Canceled).